

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 275 889 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
15.01.2003 Bulletin 2003/03

(51) Int Cl.7: **F16J 15/08**

(21) Application number: 02014941.5

(22) Date of filing: 08.07.2002

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Miyaoh, Yoshio**
Adachi-ku, Tokyo (JP)

(74) Representative:
Banzer, Hans-Jörg, Dipl.-Ing. et al
Kraus & Weisert
Patent- und Rechtsanwälte
Thomas-Wimmer-Ring 15
80539 München (DE)


(30) Priority: 13.07.2001 JP 2001213608

(71) Applicant: **ISHIKAWA GASKET CO. LTD.**
Tokyo (JP)

(54) Cylinder head gasket

(57) A cylinder head gasket (1) is formed of a single metal base plate (10) for sealing between a cylinder head and a cylinder block of an internal combustion engine. The cylinder head gasket (1) has a primary sealing portion (S1) including a grommet (11, 14) or shim (14)

around a cylinder bore, and a secondary sealing portion (S2) outside the primary sealing portion. The secondary sealing portion (S2) is formed of a bead (12) and a foamed coating layer (22) coated on one side or both sides of the bead to cover at least a portion of the bead in a belt shape.

Fig. 1

Description

Background of the Invention and Related Art Statement

[0001] The invention relates to a cylinder head gasket formed of a single metal base plate, which is installed between two members, such as a cylinder head and a cylinder block, of an internal combustion engine to seal therebetween.

[0002] When a joint surface between the cylinder head and the cylinder block (cylinder body) of the engine of the automobile is sealed, the cylinder head gasket is installed therebetween to seal combustion gas, cooling water and the like.

[0003] In view of demand for a light weight and low cost of the engine, a structure of the cylinder head gasket has been shifted to a simple type formed of a single metal base plate from a laminated type having a number of metal plates. Due to a single plate structure, only limited types of materials can be used.

[0004] In the laminated type metal plate gasket, a sealing member, such as a bead, grommet and shim, can be combined as necessity and provided in double for effective sealing. However, in the single plate gasket, a type and a number of sealing members are limited, so that a simplified sealing device has to be used. Moreover, an area available for the sealing device has been limited with reduction of an engine size.

[0005] As shown in Fig. 5, the cylinder head gasket is formed to have a shape of an engine member such as a cylinder block. The cylinder head gasket includes holes 2 for cylinder bores (hereinafter referred to simply as "cylinder bore 2"); fluid holes 3, 4 for circulating cooling water and engine oil (hereinafter referred to simply as "fluid holes 3, 4"); and bolt holes 5 for tightening bolts and the like. Also, sealing devices, such as beads 12, 13, with respect to the respective holes to be sealed are provided.

[0006] Although the same gasket is used to seal between the engine components, a different sealing property is required to seal the different holes. At the cylinder bores 2, it is required to seal the combustion gas with a high temperature and a high pressure, while a fluid with a relatively low temperature and a low pressure needs to be sealed at the fluid holes 3.

[0007] An arc shape bead 12 with a narrow width, which is formed of a material with elasticity for fitting to an irregular surface, is provided around the cylinder bore 2. Also, the cylinder bore 2 is surrounded by the bolt holes 5. Bolts are inserted into the bolt holes 5 to tighten the cylinder head and the cylinder block by applying a large pressure.

[0008] A bead 13 is provided around the fluid hole 3 to seal the same. Depending on a structure of the engine, the fluid hole 3 may be formed outside an area surrounded by the bolt holes 5. In this case, a pressing force of the tightening bolts is applied on only one side of the fluid hole 3, so that the tightening force becomes

small. To solve the problem, a higher bead, a narrower bead, or a pointed bead has been used.

[0009] Further, to seal a small uneven surface like a tool mark or the like formed on a sealing surface of the engine member, such as the cylinder head and the cylinder block, a micro seal coating made of rubber, such as a NBR rubber and a fluoro rubber, is applied to entire surfaces on both sides of the gasket.

[0010] Since the micro seal coating is generally has a hardness of 2H - 4B in pencil hardness and a thickness of 10 μm - 30 μm , the micro seal coating has a sufficient sealing effect with respect to a small uneven surface in the order of 5 μm - 15 μm , such as a tool mark left on the sealing surface of the engine member. However, the micro seal coating can not effectively seal a slightly larger uneven surface like a V-notch and a step with a 20 μm - 50 μm depth.

[0011] Especially, in the case that such a large scratch formed on the surface of the engine member crosses a sealing line formed by the bead or the like, a part of the scratch is not sufficiently sealed. Thus, the combustion gas, cooling water or oil may leak.

[0012] The leaking problem by the scratch, such as a V-notch, on the sealing surface of the engine member has been considered as a serious problem. This is because a relatively soft and fragile metal such as an aluminum alloy has been used for an engine member to reduce a weight of an engine. Also, even slight leak of the combustion gas, cooling water or oil needs to be prevented.

[0013] In view of the above problems, the present invention has been made. An object of the invention is to provide a cylinder head gasket formed of a single base plate, wherein the cylinder head gasket has a primary sealing portion having resistance to the combustion gas with a high temperature, and a secondary sealing portion for forming a seal line with an appropriate hardness to thereby obtain a good sealing ability and durability.

[0014] Further objects and advantages of the invention will be apparent from the following description of the invention.

Summary of the Invention

[0015] In order to attain the above objects, a cylinder head gasket of the present invention is structured. In the first aspect of the invention, a cylinder head gasket is formed of a single metal base plate for sealing between a cylinder head and a cylinder block of an engine. The cylinder head gasket has a primary sealing portion including a grommet or shim around a cylinder bore, and a secondary sealing portion outside the primary sealing portion. The secondary sealing portion is formed of a bead and a foamed coating layer coated on one side or both sides of the bead to cover at least a portion of the bead in a belt shape.

[0016] The metal base plate is made of such a material as annealed stainless steel, heat-treated stainless

steel (spring steel) and soft steel. The grommet or the shim is made of the annealed stainless steel, the soft steel or copper.

[0017] While the bead disposed on the secondary sealing portion is generally formed in a full bead, such as a circular arc or a trapezoidal shape, other type, such as a half bead, may be used depending on a sealing ability required for the engine.

[0018] The foamed coating layer is formed by coating a foam synthetic resin, such as a silicone resin containing micro capsules, on a surface of the metal base plate by a screenprinting at a foaming ratio of 200% - 300%, with a thickness of 100 μm - 200 μm and a width of 1 mm - 5 mm. While the foamed coating layer is applied away from the grommet or shim of the primary sealing portion with a small space therebetween, the foamed coating layer may be connected to the grommet or shim. When there is an enough space, the foamed coating layer may be disposed with an appropriate space therebetween.

[0019] According to the structure, the grommet or shim of the primary sealing portion can withstand a high temperature of the combustion gas. Moreover, the grommet or shim has hardness to prevent the gasket from creep relaxation. In the secondary sealing portion, a secondary sealing line is formed of the bead and the foamed coating layer to thereby improve the sealing effect.

[0020] Also, since the foamed coating layer of the secondary sealing portion has a thickness greater than that of a micro seal coating layer, a difference in height created by the primary sealing portion can be absorbed. Moreover, since the foamed coating layer on the gasket surface covers the bead to contact the engine members, and has a relatively soft property for fitting, a sufficient sealing effect is achieved with respect to a scratch, such as a V-notch, larger than a tool mark, formed on the sealing surface of the engine member, such as the cylinder head.

[0021] Also, since the primary sealing portion is formed of a narrow sealing device, such as the grommet or shim, it is possible to apply to a smaller area associated with a reduced size of an engine. Further, the primary sealing portion prevents the high temperature combustion gas from contacting the secondary sealing portion to thereby protect the secondary sealing portion.

[0022] As the second aspect of the invention, the cylinder head gasket has a fluid hole sealing portion provided around the fluid hole. The fluid sealing portion is formed of a bead and a foamed coating layer coated on one side or both sides of the bead to cover at least a part of the bead in a belt shape.

[0023] The bead in the fluid hole sealing portion is generally formed in a half bead, since water or oil is sealed and the pressure thereof is not high. However, depending on a sealing property required for the engine, other shape, such as a full bead, may be used.

[0024] In the above structure, the fluid hole sealing

portion can be formed by the same process as that of the secondary sealing portion of the cylinder bore, thus an additional production process can be eliminated to thereby reduce a production cost.

[0025] In the third aspect of the invention, the cylinder head gasket has a foamed coating layer in the secondary sealing portion. The foamed coating layer has a thickness thicker than that of the foamed coating layer in the fluid hole sealing portion.

[0026] The thickness of the foamed coating layer can be easily changed by a double coating process. Therefore, it is easy to design various sealing properties for the cylinder bore and the fluid hole.

[0027] Also, the foamed coating layer in the fluid hole sealing portion may have a higher foaming ratio than that in the secondary sealing portion.

[0028] In the cylinder head gasket, a micro seal coating layer is applied to the whole surface of at least one side of the cylinder head gasket where the foamed coating layer is coated. The micro seal coating is made of such a material as NBR rubber and fluoro rubber, and is applied to the substantially whole surface of the gasket by the screen printing to form a thin film having a hardness of H - 2B of pencil hardness and a thickness of 10 μm - 30 μm .

[0029] The micro seal coating provides a sealing effect with respect to an uneven surface with a micro depth of 5 μm - 15 μm , such as a tool mark left on the sealing surface of the engine members. Also, since the foamed coating can be fixed on the surface, a flow of the foamed coating and creep relaxation due to the flow can be prevented.

[0030] In the cylinder head gasket, the foamed coating layer is formed of a foamed silicone coating. The micro seal coating layer is formed of a fluorine or NBR rubber coating.

[0031] Although other materials can be used for the foamed coating layer and the micro seal coating layer, the above described combination is especially preferable in view of the sealing ability and production.

Brief Description of the Drawings

[0032]

Fig. 1 is a partial perspective view showing a cylinder head gasket;

Fig. 2 is a partial section view of the cylinder head gasket;

Figs. 3(a) - 3(f) are partial perspective views showing primary sealing portions of the cylinder head gasket, wherein Figs. 3(a) and 3(b) show structures of grommets, Fig. 3(c) and 3(d) show structures of a shim provided on one side, and Fig. 3(e) and 3(f) show structures of shims provided on both sides; Figs. 4(a) - 4(f) are partial section views showing secondary sealing portions and fluid hole sealing portions of the cylinder head gasket, wherein Fig. 4

(a) shows a structure of a full bead and foamed coating layers provided on both sides, Figs. 4(b) and 4(c) show structures of full beads and a foamed coating layer provided on one side, Fig. 4(d) shows a structure of a half bead and foamed coating layers provided on both sides, Figs. 4(e) and 4(f) show structures of half beads and a foamed coating layer provided on one side; and Fig. 5 is a plan view of the cylinder head gasket.

Detained Description of Preferred Embodiments

[0033] Hereunder, embodiments of a cylinder head gasket according to the present invention will be explained with reference to the accompanied drawings.

[0034] As shown in Fig. 5, a cylinder head gasket 1 of an embodiment according to the present invention is installed between a cylinder head and a cylinder block, i. e. a cylinder body, of an engine. The cylinder head gasket 1 seals combustion gas with a high temperature and pressure in a cylinder bore, and a fluid, such as cooling water and cooling oil, passing through a cooling water path and a cooling oil path.

[0035] Incidentally, Figs. 1 - 4(f) is explanatory schematic views. A plate thickness, a dimension of a sealing groove and a length to width ratio of the cylinder head gasket are different from the actual ones for a demonstration purpose.

[0036] As shown in Figs. 1 and 5, the cylinder head gasket 1 of the first embodiment according to the present invention is formed of a metal base plate 10 made of annealed stainless steel, heat-treated stainless steel (spring steel), soft steel or the like. The metal base plate 10 is formed to fit a shape of an engine member, such as a cylinder block, and a plurality of cylinder bores 2, fluid holes 3, 4, bolt holes 5 for tightening bolts and the like are formed therein.

[0037] In the present invention, along a circumferential edge of the cylinder bore 2 of the metal base plate 10, there is provided a grommet 11 made of an annealed stainless steel plate, soft steel plate or copper plate with a thickness of 0.1 mm - 0.15 mm to constitute a primary sealing portion S1.

[0038] Also, a full bead 12 is provided outside the primary sealing portion S1, and a foamed silicone resin containing micro capsules is coated on both sides of the full bead 12 in a belt shape. The foamed silicone resin is coated by screen printing at a foaming ratio of 200% to 300% to form foamed coating layers 22 having a thickness t2 of 100 μ m - 200 μ m and a width of 1 mm - 5 mm to cover the full bead 12. A secondary sealing portion S2 is formed of the full bead 12 and the foamed coating layers 22 provided on both sides of the full bead 12.

[0039] Also, a half bead 13 is provided on a part of the fluid holes 3, such as a cooling water hole and oil hole. The foamed silicone resin containing the micro capsules is coated in a belt shape on both sides of the half bead 13 by the screen printing at a foaming ratio of 200% -

300% to form a foamed coating layer 23 having a thickness t3 of 60 μ m - 150 μ m and a width of 1 mm - 5 mm to cover the half bead 13. A fluid hole sealing portion S3 is formed of the half bead 13 and the foamed coating layers 23 provided on both sides of the half bead 13.

[0040] The thickness t2 of the foamed coating layer 22 in the secondary sealing portion S2 is formed to be thicker than the thickness t3 of the foamed coating layer 23 of the fluid hole sealing portion S3. Also, the foaming ratio of the foamed coating layer 23 around the fluid hole sealing portion may be greater than that of the foamed coating layer 22 in the secondary sealing portion.

[0041] Further, in a cylinder head gasket 1A of the second embodiment of the invention as shown in Fig. 2, in addition to the structure of the cylinder head gasket 1 as shown in Fig. 1, a micro seal coating layer 30 having a hardness of H - 2B in pencil hardness is formed by coating a material, such as NBR rubber and fluoro rubber on substantially whole surfaces on both sides of the gasket 1 through the screen printing.

[0042] Incidentally, the dimensions of a plate thickness and the like are, for example, as follows; a diameter of a cylinder bore is 80 mm, the thickness t1 of the metal base plate 10 is 0.15 - 0.4 mm; a height h1 of the full bead 12 for the cylinder bore 2 is 0.2 - 0.3 mm; a height h2 of the half bead 13 for the fluid hole 3 is 0.2 - 0.4 mm; the thickness t2 of the foamed coating layer 22 is 100 - 200 μ m; the thickness t3 of the foamed coating layer 23 is 60 - 150 μ m; and a thickness t4 of the micro seal coating 30 is 10 - 30 μ m.

[0043] Next, other embodiments are shown in Figs. 3 (a) to 4(f). Figs. 3(a) - 3(f) show embodiments of the primary sealing portion S1, wherein in Figs. 3(a) and 3(b), grommets 11, 11A are provided, respectively; in Fig. 3(c) and 3(d), a shim 41 is provided only on one side of the metal base plate; and in Fig. 3(e) and 3(f), shims 41, 41 are provided on both sides of the metal base plate. The shim 41 has a thickness of 0.03 - 0.1 mm and is made of a material, such as annealed stainless steel, soft steel or copper.

[0044] Figs. 4(a) - 4(f) show embodiments of the secondary sealing portion S2 and the fluid hole sealing portion S3. Fig. 4(a) shows a structure of the full bead 15 and the foamed coating layers 25 applied to both sides; Fig. 4(b) and Fig. 4(c) show structures of the full bead 15 and the foamed coating layer 25 applied only on one side, respectively; Fig. 4(d) shows a structure of the half bead 16 and the foamed coating layers 26 applied on both sides; and Figs. 4(e) and 4(f) show a structure of the half beads 16 and the foamed coating layer 26 applied only on one side, respectively.

[0045] Incidentally, in the above embodiments, while the shape of the full bead 15 is represented by a circular arc shape, its shape may be a trapezoid or other shape, and the half bead 16 may also be a shape other than the one shown in the figures.

[0046] The cylinder head gasket with a necessary sealing ability depending on a type of the engine can be

designed through a combination of the primary sealing portion S1, the secondary sealing portion S2, the fluid hole sealing portion S3, with or without the micro seal coating 30, and the one-side coating or the both-side coating.

[0047] As explained above, according to the cylinder head gasket of the present invention, the following effects can be obtained. Since a combination of the hard primary sealing portion with a good heat and creep resistance, and the soft secondary sealing portion with a good fitting ability is provided around a cylinder bore, a high sealing ability can be obtained.

[0048] More specifically, since the primary sealing portion close to the combustion chamber is formed of the grommet or shim made of metal, the first sealing portion has an excellent heat resistance. Also, since the primary sealing portion is made of the hard metal, it has an excellent creep resistance to prevent an excessive decrease in torque. Moreover, the first sealing portion protects the second sealing portion.

[0049] Also, since the bead and the foamed coating layers of the second sealing portion seal the combustion gas leaked from the first sealing portion, an excellent sealing ability can be obtained.

[0050] Especially, since the foamed coating layer provided in the secondary sealing portion is thicker than the micro seal coating layer, a step produced by the primary sealing portion can be covered. A scratch, such as a V-notch, larger than a tool mark formed on the sealing surface of the member, i.e. cylinder head, can be covered by the foamed coating layer, which is relatively soft and has a fitting property, so that a good sealing ability can be obtained.

[0051] Also, since the fluid hole sealing portion is formed of the same bead and foamed coating layer as those in the secondary sealing portion, the fluid hole sealing portion can be formed at the same time in the same process as the secondary sealing portion, thus an additional production processes is eliminated to thereby reduce a production cost.

[0052] Therefore, a cylinder head gasket of a single plate having a good sealing ability, heat resistance and durability can be obtained.

Claims

1. A metal gasket (1) for an internal combustion engine with at least one cylinder bore and a plurality of fluid holes to be sealed, comprising:

a metal plate (10) extending throughout an entire area to be sealed and having a first hole (2) corresponding to the cylinder bore and at least one second hole (3, 4) corresponding to the fluid holes,

a primary sealing portion (S1) disposed around the first hole and formed of one of a grommet

(11, 11A) and a shim (41), and a first bead (12) formed around the primary sealing portion to surround the same, said metal gasket (1) being **characterized in that** a first foamed coating layer (22) is disposed on at least one of two sides of the first bead.

2. A metal gasket (1) according to claim 1, further comprising a fluid hole sealing portion (S3) disposed around the at least one second hole (3, 4) and formed of a second bead (13) having two sides, and a second foamed coating layer (23) disposed on at least one of the two sides of the second bead.
3. A metal gasket (1) according to claim 2, wherein said first foamed coating layer (22) has a thickness greater than that of the second foamed coating layer (23).
4. A metal gasket (1) according to claim 2 or 3, wherein said first and second foamed coating layers (22, 23) are formed of a foamed material with a predetermined foaming ratio.
5. A metal gasket (1) according to any one of claims 2 to 4, wherein said first foamed coating layer (22) has a foaming ratio less than that of the second foamed coating layer (23).
6. A metal gasket (1) according to any one of claims 1 to 5, further comprising a micro seal coating (30) disposed on a substantially entire surface of the metal gasket.

Fig. 1




Fig. 2




Fig. 3(a)




Fig. 3(b)




Fig. 3(c)




Fig. 3(d)




Fig. 3(e)




Fig. 3(f)




Fig. 4(a)




Fig. 4(b)




Fig. 4(c)




Fig. 4(d)




Fig. 4(e)




Fig. 4(f)






Fig. 5





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 275 889 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
21.01.2004 Bulletin 2004/04

(51) Int Cl.7: **F16J 15/08**

(43) Date of publication A2:
15.01.2003 Bulletin 2003/03

(21) Application number: **02014941.5**

(22) Date of filing: **08.07.2002**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
IE IT LI LU MC NL PT SE SK TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **Miyaoh, Yoshio**
Adachi-ku, Tokyo (JP)

(74) Representative:
Banzer, Hans-Jörg, Dipl.-Ing. et al
Kraus & Weisert
Patent- und Rechtsanwälte
Thomas-Wimmer-Ring 15
80539 München (DE)

(30) Priority: **13.07.2001 JP 2001213608**


(71) Applicant: **ISHIKAWA GASKET CO. LTD.**
Tokyo (JP)

(54) **Cylinder head gasket**

(57) A cylinder head gasket (1) is formed of a single metal base plate (10) for sealing between a cylinder head and a cylinder block of an internal combustion engine. The cylinder head gasket (1) has a primary sealing portion (S1) including a grommet (11, 14) or shim (14)

around a cylinder bore, and a secondary sealing portion (S2) outside the primary sealing portion. The secondary sealing portion (S2) is formed of a bead (12) and a foamed coating layer (22) coated on one side or both sides of the bead to cover at least a portion of the bead in a belt shape.

Fig. 1



EP 1 275 889 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 02 01 4941

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	US 5 938 208 A (ABE YOSHITAKA ET AL) 17 August 1999 (1999-08-17) * column 3, line 32 - column 7, line 3; figures 3-6,14-17 *	1-6	F16J15/08
Y	GB 2 169 362 A (LECHLER ELRING DICHUNGWERKE) 9 July 1986 (1986-07-09) * page 1, line 27 - page 4, line 5; figures 1-3 *	1-6	
A	EP 0 592 142 A (NICHIAS CORP) 13 April 1994 (1994-04-13) * column 1, line 34 - column 3, line 29; figures 3-11 *	1	
A	EP 0 833 087 A (ISHIKAWA GASKET) 1 April 1998 (1998-04-01) * column 4, line 1-9; figure 3 *	5	
A	EP 0 094 616 A (NIHON METAL GASKET) 23 November 1983 (1983-11-23) * page 7, line 7 - page 9, line 18; figure 3 *	6	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			F16J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 3 December 2003	Examiner Mauriès, L
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03/02 (P4/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 02 01 4941

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

03-12-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5938208	A	17-08-1999	NONE	
GB 2169362	A	09-07-1986	DE 3500071 A1	03-07-1986
EP 0592142	A	13-04-1994	JP 6032836 U	28-04-1994
			DE 69308259 D1	03-04-1997
			DE 69308259 T2	12-06-1997
			EP 0592142 A1	13-04-1994
EP 0833087	A	01-04-1998	US 5769430 A	23-06-1998
			EP 0833087 A1	01-04-1998
			JP 10103521 A	21-04-1998
EP 0094616	A	23-11-1983	JP 1768362 C	30-06-1993
			JP 2006376 B	08-02-1990
			JP 58200858 A	22-11-1983
			JP 58200859 A	22-11-1983
			JP 63050589 B	11-10-1988
			DE 3373129 D1	24-09-1987
			EP 0094616 A1	23-11-1983
			KR 8802631 B1	07-12-1988
			US 4799695 A	24-01-1989

EPO FORM P0168

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82